Page 2 of 21

Serial No.: 10/663,926 Confirmation No.: 2299 Filed: September 16, 2003

For: COMPOUNDS CONTAINING QUATERNARY CARBONS AND SILICON-CONTAINING GROUPS,

MEDICAL DEVICES, AND METHODS

Amendments to the Claims

This listing of claims replaces all prior versions, and listings, of claims in the aboveidentified application:

1. (Currently Amended) A medical device comprising a segmented polymer comprising a soft segment comprising a group of the formula:

$$-[-(R^1)_n-(-Z-(R^2)_m-)_p-(-Si(R)_2-V_r-)_g-]_{q^n}$$

wherein:

n = 0 or 1; m = 0 or 1; p = 1-100,000; r = 0-100,000; s = 1-100,000; q = 1-100,000;

R¹ and R² are each independently a saturated or unsaturated aliphatic group, an aromatic group, or combinations thereof, optionally including heteroatoms;

Z is $-C(R^3)_2$ — wherein each R^3 is independently a saturated or unsaturated aliphatic group, an aromatic group, or combinations thereof, optionally including heteroatoms, wherein the two R^3 groups within $-C(R^3)_2$ - can be optionally joined to form a ring;

each R is independently a saturated or unsaturated aliphatic group, an aromatic group, or combinations thereof, optionally including heteroatoms; and

V is
$$[[-O-Si(R)_2-or]] R^1$$
;

with the proviso that the polymer is [[substantially]] free of carbonate linkages.

2. (Original) The medical device of claim 1 wherein p = 1-5000.

Page 3 of 21

Serial No.: 10/663,926 Confirmation No.: 2299 Filed: September 16, 2003

For: COMPOUNDS CONTAINING QUATERNARY CARBONS AND SILICON-CONTAINING GROUPS,

MEDICAL DEVICES, AND METHODS

- 3. (Original) The medical device of claim 2 wherein p = 2-12.
- 4. (Original) The medical device of claim 1 wherein R¹ and R² are each independently a straight chain alkylene group, an arylene group, or combinations thereof.
- 5. (Original) The medical device of claim 4 wherein R¹ and R² are each independently a straight chain alkylene group.
- 6. (Original) The medical device of claim 1 wherein R¹ and R² are each independently groups containing up to 100 carbon atoms.
- 7. (Original) The medical device of claim 6 wherein R¹ and R² are each independently groups containing up to 20 carbon atoms.
- 8. (Original) The medical device of claim 7 wherein R¹ and R² are each independently groups containing 2 to 20 carbon atoms.
- 9. (Currently Amended) The medical device of claim 1 wherein each R³ is independently a straight chain alkyl group, an aryl group, or combinations thereof, optionally including heteroatoms.
- 10. (Currently Amended) The medical device of claim 9 wherein each R³ is independently a straight chain alkyl group, optionally including heteroatoms.
- 11. (Original) The medical device of claim 10 wherein each R³ is independently a straight chain alkyl group containing 1 to 20 carbon atoms.

Page 4 of 21

Serial No.: 10/663,926 Confirmation No.: 2299 Filed: September 16, 2003

For: COMPOUNDS CONTAINING QUATERNARY CARBONS AND SILICON-CONTAINING GROUPS,

MEDICAL DEVICES, AND METHODS

- 12. (Original) The medical device of claim 1 wherein the polymer further comprises a urethane group, a urea group, or combinations thereof.
- 13. (Original) The medical device of claim 12 wherein the polymer comprises a segmented polyurethane.
- 14. (Original) The medical device of claim 1 wherein the polymer is a biomaterial.
- 15. (Currently Amended) The medical device of claim 14 wherein the polymer is [[substantially]] free of ether, ester, and carbonate linkages.
- 16. (Original) The medical device of claim 1 wherein the polymer is linear, branched, or crosslinked.
- 17. (Currently Amended) A medical device comprising a segmented polymer comprising a soft segment prepared from a compound of the formula:

$$Y-[-(R^{\dagger})_{n}-(-Z-(R^{2})_{m}-)_{p}-(-Si(R)_{2}-V_{r}-)_{s}-]_{q}-R^{5}-Y$$

wherein:

each Y is independently OH or NR4H;

n = 0 or 1;

m = 0 or 1;

p = 1-100,000;

r = 0-100,000;

s = 1-100,000;

q = 1-100,000;

R¹, R², and R⁵ are each independently a saturated or unsaturated aliphatic group, an aromatic group, or combinations thereof; optionally including heteroatoms;

Page 5 of 21

Serial No.: 10/663,926 Confirmation No.: 2299 Filed: September 16, 2003

For: COMPOUNDS CONTAINING QUATERNARY CARBONS AND SILICON-CONTAINING GROUPS,

MEDICAL DEVICES, AND METHODS

Z is $-C(R^3)_2$ - wherein each R^3 is independently a saturated or unsaturated aliphatic group, an aromatic group, or combinations thereof, optionally including heteroatoms, wherein the two R^3 groups within $-C(R^3)_2$ - can be optionally joined to form a ring;

each R is independently a saturated or unsaturated aliphatic group, an aromatic group, or combinations thereof, optionally including heteroatoms;

each R⁴ is independently H or a saturated or unsaturated aliphatic group, an aromatic group, or combinations thereof; and

V is [[-O-Si(R)2- or]] R';

- 18. (Original) The medical device of claim 17 wherein p = 1-100.
- 19. (Original) The medical device of claim 18 wherein p = 2-12.
- 20. (Original) The medical device of claim 17 wherein the number average molecular weight of the compound of the formula $Y-[-(R^1)_n-(-Z-(R^2)_m-)_p-(-Si(R)_2-V_r-)_n-]_q-R^5-Y$ is no greater than about 100,000 grams/mole.
- 21. (Original) The medical device of claim 20 wherein the number average molecular weight of the compound of the formula Y-[-(R¹)_n-(-Z-(R²)_m-)_p-(-Si(R)₂-V_r-)_s-]_q-R⁵-Y is about 1000 grams/mole to about 1500 grams/mole.
- 22. (Original) The medical device of claim 17 wherein R¹ and R² are each independently a straight chain alkylene group, an arylene group, or combinations thereof.
- 23. (Original) The medical device of claim 22 wherein R¹ and R² are each independently a straight chain alkylene group.

Page 6 of 21

Serial No.: 10/663,926 Confirmation No.: 2299 Filed: September 16, 2003

For: COMPOUNDS CONTAINING QUATERNARY CARBONS AND SILICON-CONTAINING GROUPS,

MEDICAL DEVICES, AND METHODS

- 24. (Original) The medical device of claim 17 wherein R¹ and R² are each independently groups containing up to 100 carbon atoms.
- 25. (Original) The medical device of claim 24 wherein R¹ and R² are each independently groups containing up to 20 carbon atoms.
- 26. (Original) The medical device of claim 25 wherein R¹ and R² are each independently groups containing 2 to 20 carbon atoms.
- 27. (Original) The medical device of claim 17 wherein each R² includes at least two carbon atoms.
- 28. (Currently Amended) The medical device of claim 17 wherein each R³ is independently a straight chain alkyl group, an aryl group, or combinations thereof, optionally including heteroatoms.
- 29. (Currently Amended) The medical device of claim 28 wherein each R³ is independently a straight chain alkyl group, optionally including heteroatoms.
- 30. (Original) The medical device of claim 29 wherein each R³ is independently a straight chain alkyl group containing 1 to 20 carbon atoms.
- 31. (Original) The medical device of claim 17 wherein the polymer further comprises a urethane group, a urea group, or combinations thereof.
- 32. (Original) The medical device of claim 31 wherein the polymer comprises a segmented polymethane.

Page 7 of 21

Serial No.: 10/663,926 Confirmation No.: 2299 Filed: September 16, 2003

For: COMPOUNDS CONTAINING QUATERNARY CARBONS AND SILICON-CONTAINING GROUPS,

MEDICAL DEVICES, AND METHODS

- 33. (Original) The medical device of claim 17 wherein the polymer is a biomaterial.
- 34. (Currently Amended) The medical device of claim 33 wherein the polymer is [[substantially]] free of ether, ester, and carbonate linkages.
- 35. (Original) The medical device of claim 17 wherein each Y is OH.
- 36. (Original) The medical device of claim 17 wherein each R⁴ is independently H or a straight chain alkyl group.
- 37. (Original) The medical device of claim 36 wherein each R⁴ is independently a straight chain alkyl group containing 1 to 20 carbon atoms.
- 38. (Original) The medical device of claim 36 wherein each R⁴ is H.
- 39. (Original) The medical device of claim 17 wherein the polymer is linear, branched, or crosslinked.
- 40. (Currently Amended) A segmented polymer comprising a soft segment comprising a group of the formula:

$$-[-(R^1)_n-(-Z-(R^2)_m-)_p-(-Si(R)_2-V_r-)_s-]_q$$

wherein:

$$n = 0 \text{ or } 1;$$
 $m = 0 \text{ or } 1;$
 $p = 1-100,000;$
 $r = 0-100,000;$

Page 8 of 21

Serial No.: 10/663,926 Confirmation No.: 2299 Filed: September 16, 2003

For: COMPOUNDS CONTAINING QUATERNARY CARBONS AND SILICON-CONTAINING GROUPS.

MEDICAL DEVICES, AND METHODS

s = 1-100,000;

q = 1-100,000;

R¹ and R² are each independently a saturated or unsaturated aliphatic group, an aromatic group, or combinations thereof, optionally including heteroatoms;

Z is $-C(R^3)_3$ - wherein each R^3 is independently a saturated or unsaturated aliphatic group, an aromatic group, or combinations thereof, optionally including heteroatoms, wherein the two R^3 groups within $-C(R^3)_2$ - can be optionally joined to form a ring;

each R is independently a saturated or unsaturated aliphatic group, an aromatic group, or combinations thereof, optionally including heteroatoms; and

V is $[[-O-Si(R)_2-or]] R^1$;

- 41. (Original) The polymer of claim 40 wherein p = 1-5000.
- 42. (Original) The polymer of claim 40 wherein p = 2-12.
- 43. (Original) The polymer of claim 40 wherein R¹ and R² are each independently a straight chain alkylene group, an arylene group, or combinations thereof.
- 44. (Original) The polymer of claim 43 wherein R¹ and R² are each independently a straight chain alkylene group.
- 45. (Original) The polymer of claim 40 wherein R¹ and R² are each independently groups containing 2 to 20 carbon atoms.
- 46. (Currently Amended) The polymer of claim 40 wherein each R³ is independently a straight chain alkyl group, an aryl group, or combinations thereof, optionally including heteroatoms.

Page 9 of 21

Serial No.: 10/663,926 Confirmation No.: 2299 Filed: September 16, 2003

For: COMPOUNDS CONTAINING QUATERNARY CARBONS AND SILICON-CONTAINING GROUPS.

MEDICAL DEVICES, AND METHODS

- 47. (Currently Amended) The polymer of claim 46 wherein each R³ is independently a straight chain alkyl group, optionally including heteroatoms.
- 48. (Original) The polymer of claim 47 wherein each R³ is independently a straight chain alkyl group containing 1 to 20 carbon atoms.
- 49. (Original) The polymer of claim 40 which is linear, branched, or crosslinked.
- 50. (Currently Amended) A segmented polymer comprising a urethane group, a urea group, or combinations thereof, and a soft segment comprising a group of the formula:

$$-[-(R^{1})_{n}-(-Z-(R^{2})_{m}-)_{p}-(-Si(R)_{2}-V_{r}-)_{s}-]_{q}-$$
wherein:
$$n = 0 \text{ or } 1;$$

$$m = 0 \text{ or } 1;$$

$$p = 1-100,000;$$

$$r = 0-100,000;$$

$$s = 1-100,000;$$

$$q = 1-100,000;$$

R¹ and R² are each independently a saturated or unsaturated aliphatic group, an aromatic group, or combinations thereof, optionally including heteroatoms;

Z is $-C(R^3)_2$ - wherein each R^3 is independently a saturated or unsaturated aliphatic group, an aromatic group, or combinations thereof, optionally including heteroatoms, wherein the two R^3 groups within $-C(R^3)_2$ - can be optionally joined to form a ring;

each R is independently a saturated or unsaturated aliphatic group, an aromatic group, or combinations thereof; optionally including heteroatoms; and

$$V \text{ is } [[-O-Si(R)_2-or]] R^1;$$

Page 10 of 21

Serial No.: 10/663,926 Confirmation No.: 2299 Filed: September 16, 2003

For: COMPOUNDS CONTAINING QUATERNARY CARBONS AND SILICON-CONTAINING GROUPS,

MEDICAL DEVICES, AND METHODS

- 51. (Original) The polymer of claim 50 wherein p = 1-100.
- 52. (Original) The polymer of claim 51 wherein p = 2-12.
- 53. (Original) The polymer of claim 50 which is a segmented polyurethane.
- 54. (Original) The polymer of claim 50 which is a biomaterial.
- 55. (Currently Amended) The polymer of claim 54 which is [[substantially]] free of ether, ester, and carbonate linkages.
- 56. (Original) The polymer of claim 50 which is linear, branched, or crosslinked.
- 57. (Previously presented) A segmented polymer comprising a soft segment prepared from a compound of the formula:

$$Y-[-(R^1)_n-(-Z-(R^2)_m-)_p-(-Si(R)_2-V_r-)_s-]_q-R^5-Y$$

wherein:

each Y is independently OH or NR4H;

n = 0 or 1;

m = 0 or 1;

p = 1-100,000;

r = 0-100,000;

s = 1-100,000;

q = 1-100,000;

R¹, R², and R⁵ are each independently a saturated or unsaturated aliphatic group, an aromatic group, or combinations thereof, optionally including heteroatoms;

Page 11 of 21

Serial No.: 10/663,926 Confirmation No.: 2299 Filed: September 16, 2003

For: COMPOUNDS CONTAINING QUATERNARY CARBONS AND SILICON-CONTAINING GROUPS,

MEDICAL DEVICES, AND METHODS

Z is $-C(R^3)_2$ - wherein each R^3 is independently a saturated or unsaturated aliphatic group, an aromatic group, or combinations thereof, optionally including heteroatoms, wherein the two R^3 groups within $-C(R^3)_2$ - can be optionally joined to form a ring;

each R is independently a saturated or unsaturated aliphatic group, an aromatic group, or combinations thereof, optionally including heteroatoms;

each R⁴ is independently H or a saturated or unsaturated aliphatic group, an aromatic group, or combinations thereof; and

V is $[[-O-Si(R)_2-or]] R^1$;

- 58. (Original) The polymer of claim 57 wherein p = 1-100.
- 59. (Original) The polymer of claim 58 wherein p = 2-12.
- 60. (Original) The polymer of claim 57 wherein the number average molecular weight of the compound of the formula Y-[- $(R^1)_n$ -(-Z- $(R^2)_m$ -)_p-(- $Si(R)_2$ -V_r-)_s-]_q-R⁵-Y is no greater than about 100,000 grams/mole.
- 61. (Original) The polymer of claim 57 wherein R¹ and R² are each independently a straight chain alkylene group, an arylene group, or combinations thereof.
- 62. (Original) The polymer of claim 61 wherein R¹ and R² are each independently groups containing up to 100 carbon atoms.
- 63. (Original) The polymer of claim 62 wherein R¹ and R² are each independently groups containing up to 20 carbon atoms.

Page 12 of 21

Serial No.: 10/663,926 Confirmation No.: 2299 Filed: September 16, 2003

For: COMPOUNDS CONTAINING QUATERNARY CARBONS AND SILICON-CONTAINING GROUPS,

MEDICAL DEVICES, AND METHODS

- 64. (Original) The polymer of claim 63 wherein R¹ and R² are each independently groups containing 2 to 20 carbon atoms.
- 65. (Original) The polymer of claim 57 wherein each R² includes at least two carbon atoms.
- 66. (Currently Amended) The polymer of claim 57 wherein each R³ is independently a straight chain alkyl group, an aryl group, or combinations thereof, optionally including heteroatoms.
- 67. (Original) The polymer of claim 66 wherein each R³ is independently a straight chain alkyl group containing 1 to 20 carbon atoms.
- 68. (Original) The polymer of claim 57 wherein each Y is OH.
- 69. (Original) The polymer of claim 57 wherein each R⁴ is independently H or a straight chain alkyl group.
- 70. (Original) The polymer of claim 57 which is linear, branched, or crosslinked.
- 71-75. (Cancelled)
- 76. (Currently Amended) A method of making a segmented polymer comprising a soft segment comprising a group of the formula

$$-[-(R^{1})_{11}-(-Z-(R^{2})_{11}-)_{12}-(-Si(R)_{2}-V_{r}-)_{2}-]_{q}-$$

the method comprising combining an organic compound containing two or more groups capable of reacting with hydroxyl or amine groups with a polymeric starting compound of the formula:

Page 13 of 21

Serial No.: 10/663,926 Confirmation No.: 2299 Filed: September 16, 2003

For: COMPOUNDS CONTAINING QUATERNARY CARBONS AND SILICON-CONTAINING GROUPS,

MEDICAL DEVICES, AND METHODS

$$Y-[-(R^1)_n-(-Z-(R^2)_m-)_p-(-Si(R)_2-V_{r-})_s-]_q-R^5-Y$$

wherein:

each Y is independently OH or NR⁴H;

n = 0 or 1;

m = 0 or 1;

p = 1-100,000;

r = 0-100,000;

q = 1-100,000;

R¹, R², and R⁵ are each independently a saturated or unsaturated aliphatic group, an aromatic group, or combinations thereof, optionally including heteroatoms;

Z is $-C(R^3)_2$ - wherein each R^3 is independently a saturated or unsaturated aliphatic group, an aromatic group, or combinations thereof; optionally including heteroatoms, wherein the two R^3 groups within $-C(R^3)_2$ - can be optionally joined to form a ring;

each R is independently a saturated or unsaturated aliphatic group, an aromatic group, or combinations thereof, optionally including heteroatoms;

each R⁴ is independently H or a saturated or unsaturated aliphatic group, an aromatic group, or combinations thereof; and

V is $[[-O-Si(R)_2-or]]R^1$;

with the proviso that the polymer is [[substantially]] free of carbonate linkages.

77. (Currently Amended) The method of claim 76 wherein the polymeric starting compound is prepared by a method comprising:

combining monomers of Formula II [[or]] and Formula III;

Page 14 of 21

Serial No.: 10/663,926 Confirmation No.: 2299 Filed: September 16, 2003

For: COMPOUNDS CONTAINING QUATERNARY CARBONS AND SILICON-CONTAINING GROUPS,

MEDICAL DEVICES, AND METHODS

$$R^{10}HC = CH - (R^{11})_{r} - (-Si(R)_{2} - V_{r})_{s} - (R^{12})_{s} - CH = CHR^{13}$$
 (II)

$$R^{10}HC=CH-(R^{11})_{r}-Z-(R^{12})_{s}-CH=CHR^{13}$$
 (III)

wherein:

r, s, V, Z, and R are as defined [[above]] in claim 76; r' = 0 or 1; s' = 0 or 1;

R¹⁰ and R¹³ are each independently hydrogen or straight chain, branched, or cyclic alkyl groups containing up to 6 carbon atoms; and

R¹¹ and R¹² are each independently a saturated aliphatic group, an aromatic group, or combinations thereof;

with an alkene metathesis catalyst, and optionally applying a vacuum_

before adding the alkene metathesis catalyst, or the method includes allowing the monomers to polymerize in the presence of the alkene metathesis catalyst prior to adding a chain transfer agent.